



Structural heterogeneity in calcium aluminosilicate glasses

Moesgaard, Mette; Keding, Ralf; Skibsted, Jørgen; Yue, Yuanzheng

Publication date:
2010

Document Version
Early version, also known as pre-print

[Link to publication from Aalborg University](#)

Citation for published version (APA):

Moesgaard, M., Keding, R., Skibsted, J., & Yue, Y. (2010). *Structural heterogeneity in calcium aluminosilicate glasses*. Abstract from 2010 Glass and Optical Materials Division Annual Meeting.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Structural heterogeneity in calcium aluminosilicate glasses

Mette Moesgaard^a, Ralf Keding^a, Jørgen Skibsted^b, Yuanzheng Yue^a*

^a Section of Chemistry, Aalborg University, DK-9000 Aalborg, Denmark

^b Department of Chemistry, Aarhus University, DK-8000 Århus, Denmark

The physical and chemical properties of glasses are determined largely by their microstructure in both short- and intermediate-range. Despite numerous studies on the intermediate-range order (IRO), some key questions still remain unanswered. In this work, we investigate the IRO of peralkaline glasses within the calcium aluminosilicate system. This is performed by structural modeling and solid-state ²⁹Si and ²⁷Al nuclear magnetic resonance (NMR) spectroscopy. Two structural modeling approaches are proposed to describe the IRO. One model assumes a random spatial arrangement of Al, whereas the other allows clustering of regions rich in highly polymerized AlO₄ and SiO₄ units and other regions rich in highly depolymerized SiO₄ units. The clustering is described as IRO heterogeneity and this modeling approach provides a good description of the NMR spectra for all glasses. In contrast, the first approach can not convincingly model the NMR data. Thus, structural heterogeneities in the IRO do exist in the studied glasses.

Key words:

Calcium aluminosilicates

Structural modeling

Intermediate-range order

MAS NMR spectroscopy